

Penteco GN - 150 150 mil Geonet Biplanar

- ❖ **Drainage**
- ❖ **Leak Detection**
- ❖ **Gas Mitigation**
- ❖ **Protection**

Geonets are made from high-density polyethylene (HDPE) strands diagonally parallel to one another. This biplanar structure allows for liquid or gases to flow in any direction through the horizontal plane of the mesh.

Geonets are almost exclusively used as leak detection layers within geomembrane containment systems. The geonet is typically installed in between the two layers of geomembrane to allow for potential leaks to flow directly to the sump collection system. If the drainage median has the potential of getting clogged (sediments/ fines), then its best to use a geocomposite.

GN - 150			M.A.R.V	
Property	Test Method	Frequency	Imperial	Metric
Thickness (min.avg)	ASTM D-5199	1/50,000 ft ² (1/4,600 m ²)	150 mil	3.81 mm
Transmissivity	ASTM D-4716	1/540,000 ft ² (1/50,000 m ²)	4.83 gal/min/ft	1 x 10 ⁻³ m ² /sec
Density (min.)	ASTM D-792	1/50,000 ft ² (1/4,600 m ²)	0.94 g/cm ³	0.94 g/cm ³
Peak Tensile Strength (MD)	ASTM D-7179	1/50,000 ft ² (1/4,600 m ²)	30 lbs/in	5.2 N/mm
Carbon Black Content	ASTM D-4218	1/50,000 ft ² (1/4,600 m ²)	2.0%	2.0%
Dimensions				
Typical Roll Size	Measured		14.50 ft x 300 ft	4.42 m x 91.4 m
Area	Calculated		4350 ft ²	404 m ²

Notes:

- (1) Roll Lengths may vary depending on the manufacturer. All roll widths/lengths have a tolerance of ±1 %.
- (2) Custom roll lengths can be ordered. Transportation cost might be affected.
- (3) Penteco is a distributor for this product with manufacturing partners based out of Canada & USA.
- (4) Manufacturer data sheet provided at time of purchase.

DISCLAIMER: The data above represents the manufacturer's laboratory testing of their product. It is the user's responsibility to determine the suitability of the products. Penteco is a distributor for these products through its manufacturing partners. Penteco will provide the manufacturers data sheet at the time of sale. There may be very slight variation, but overall, the data represents standard industry specifications. Penteco and manufacturing partners assume no liability, nor can they provide any warranty, without having additional information regarding the use of the products. The same goes for any infringement on patents - no permission can be granted without further disclosure.